

Architectural in-plant Colorants for Solvent Based Applications

General Description

COLORTREND[®] Alkyd E Colorants are high-strength, pourable color pastes recommended for in-plant tinting of solvent-based architectural coatings. All colorants have a minimum fineness of grind Hegman Gauge (<20 um) which make COLORTREND[®] Alkyd E Colorants ideal for the tinting of solvent-based coatings.

The colorants are cost-effective, high concentration products dispersed in a long oil alkyd resin. They contain high quality CI pigments that many paint formulating professionals want to use. Strength is controlled to $\pm 3\%$ vs. standard, $\Delta E < 1$ vs. standard.

The colorants contain synergistic combinations of wetting and dispersing agents which allow them to mix readily into Alkyd based products.

COLORTREND[®] Alkyd E products provide an alternative for in-house grinding. The dispersion stage of paint manufacture for many paint companies is a time consuming process that has the potential to reduce production efficiency and increase cost.

The use of dispersions provides a solution for these issues by reducing cycle times to maximize production output and flexibility, while minimizing complexity.



COLORTREND® ALKYD-E Typical Physical Properties

Masstone	Tint	Product Code	Description	CI Pigment Reference	Specific Gravity	Pigment Solids	Lightfastness (Approx)		Alkaline Fastness
							1:1	1:25	
		019010	E White	White 6	1.80	64.0	8	8	5
		019011	E Organic Red	Red 112	0.98	26.0	7	6	5
		019012	E Red Oxide	Red 101	1.78	59.7	8	8	5
		019013	E Yellow Oxide	Yellow 42	1.44	49.1	8	8	5
		019014	E Raw Umber	Brown 7	1.22	40.0	8	8	5
		019015	E Organic Yellow	Yellow 74	1.02	28.7	6-7	4-5	5
		019016	E Medium Yellow	Yellow 83	0.99	26.0	6-7d*	4-5	5
		019017	E Phthalo Green	Green 7	1.05	26.0	8	8	5
		019018	E Phthalo Blue	Blue 15:2	1.02	27.2	8	8	5
		019019	E Red Violet	Violet 19	0.95	10.5	6-7d*	7	5
		019020	E Black	Black 7	1.01	23.0	8	8	5

All data obtained directly from pigment suppliers, individual testing is recommended. Lightfastness is measured against the blue wool standard on a scale of 1 to 8 where 1 = severe change and 8 = no change.

Locations

America

Chromaflo Technologies Corp

2600 Michigan Avenue
P.O. Box 816
Ashtabula, Ohio
44005 USA
PHONE: +1 440 997-5137
www.chromaflo.com

Europe

Chromaflo Technologies B.V.

Ankerkade 101
6222 NL Maastricht
Netherlands
PHONE: +31 43 352-7700

Asia-Pacific

Chromaflo Technologies Australia Pty Ltd

30-32 Commercial Drive
P.O. Box 996 Dandenong
3175 Victoria Australia
PHONE: +61 3 9703-8888

Malaysia

Malaysia Representative Office

11, Jalan Pelukis U1/46
Temasya Industrial Park,
Glenmarie 40150
Shah Alam, Selangor,
Malaysia
PHONE: +603 5567 0867

China

Chromaflo Technologies China Ltd.

No.655. Shenfu Road,
XinZhuang Industrial Zone,
Shanghai, 201108
P.R.China
PHONE: +86 21 2416 9200

Thailand

Thailand Representative Office

Regus Sathorn Square
No. 3769, 37th Floor,
98 North Sathorn Road
Silom, Bangrak,
Bangkok 10500
Thailand
PHONE: +668 7088 0500

India

Chromaflo Technologies India Pty Ltd

J-15 Taloja MIDC,
Taloja,
Raigad District, Maharashtra State
India 410208
PHONE: +91 22 2778 8521

South Africa

Chromaflo Technologies Africa

17 Crusher Road
Crown Ext. 3
Johannesburg 2095
South Africa
PHONE: +27 11 084 1600



Health & Safety
OHSAS 18001
SAI GLOBAL



Quality
ISO 9001
SAI GLOBAL



Environment
ISO 14001
SAI GLOBAL

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

